

EQUIVALENCES DES DURETES

Choisissez la valeur à convertir

Entrez une valeur dans la case correspondante



PARAMETRES

<input checked="" type="radio"/>	Dureté HB :	
<input type="radio"/>	RM :	
<input type="radio"/>	Dureté HRC :	
<input type="radio"/>	Dureté HV :	

DURETE HB	DURETE HRC	DURETE HV	RM
UNE	VALEUR	CORRECTE	!!!

Rm N/mm ²	Dureté HB	Dureté HRC	Dureté HV
590	176		190
600	179		194
610	182		197
620	186		200
630	186		204
640	192		207
645	195		209
655	198		212
665	202		216
675	205		219
685	208		223
695	211		226
705	214		229
715	216		231
725	220		235
735	223		238
745	226	20	242
755	229		244
765	232	21	248
775	233		251
785	239	22	254
795	241	23	257
805	245		261
815	248	24	264
825	251		266
835	253	25	269